

Test Report

Report No. SCL03J000377005

Page 1 of 5

Applicant ZHONGSHAN FUZHOU ADHESIVE-PRODUCT CO.,LTD
Address TORCH HIGH-TECH DEVELOPMENT ZONE,ZHONGSHAN CITY,GUANGDONGPROVINCE CHINA

The following sample(s)and sample information was/were submitted and identified by/on the behalf of the client

Sample Name 荧光纸 fluprescent paper
Client Reference Information Y-R/Y-P/Y-O/Y-Y/Y-G/Y-OR
Sample Received Date Jan. 19, 2017
Testing Period Jan. 19, 2017 to Jan. 24, 2017

Test Requested As specified by client, to test Polycyclic Aromatic Hydrocarbons(PAHs) in the submitted sample(s).

Test Method

Test Item(s)	Test Method	Measured Equipment(s)
Polycyclic Aromatic Hydrocarbons(PAHs)	AfPS GS 2014:01 PAK	GC-MS

Test Result(s) Please refer to the following page(s).

Conclusion

Tested Item	Standard	Result
Polycyclic Aromatic Hydrocarbons (PAHs)	AfPS GS 2014:01 PAK, Category 3	Pass

Tested by Guangneng Yang

Reviewed by Wenjun Wang

Approved by Qinghong Wan

Date Jan. 26, 2017



Qinghong Wan
Technical Manager

No. R131026993

Centre Testing International Group Co.,Ltd. Shunde Branch
9/F, Pongying Building, Section 2, No.8, East of Rongqi Avenue, Ronggui, Shunde District, Foshan, Guangdong, China

Test Report

Report No. SCL03J000377005

Page 2 of 5

Limits for PAHs content (mg/kg) for material of (grip) surfaces, which are to be categorized on account of the results of the risk analysis.

Parameters	Category 1	Category 2		Category 3	
	Materials intended to be put in the mouth or materials of toys with foreseeable long-term skin contact (longer than 30 seconds)	Materials not covered by category 1, with foreseeable skin contact for longer than 30 seconds (long-term skin contact) or repeated short-term skin contact #	Toys covered by Directive 2009/48/EC	Other products	Toys covered by Directive 2009/48/EC
Benzo[a]pyrene	<0.2	<0.2	<0.5	<0.5	<1
Benzo[e]pyrene	<0.2	<0.2	<0.5	<0.5	<1
Benzo[a]anthracene	<0.2	<0.2	<0.5	<0.5	<1
Benzo[b]fluoranthene	<0.2	<0.2	<0.5	<0.5	<1
Benzo[j]fluoranthene	<0.2	<0.2	<0.5	<0.5	<1
Benzo[k]fluoranthene	<0.2	<0.2	<0.5	<0.5	<1
Chrysene	<0.2	<0.2	<0.5	<0.5	<1
Dibenz[a,h]anthracene	<0.2	<0.2	<0.5	<0.5	<1
Benzo[g,h,i]perylene	<0.2	<0.2	<0.5	<0.5	<1
Indenol[1,2,3-cd]pyrene	<0.2	<0.2	<0.5	<0.5	<1
Acenaphthylene, Acenaphthene, Fluorene, Phenanthrene, Anthracene, Fluoranthene Pyrene	<1 Sum	<5 Sum	<10 Sum	<20 Sum	<50 Sum
Naphthalene	<1	<2		<10	
Sum 18 PAHs	<1	<5	<10	<20	<50

Formulation "of repeated short-term skin contact" REACH Annex XVII No. 50 supplement (REGULATION (EU) No.1272/2013)

Test Report

Report No. SCL03J000377005

Page 3 of 5

Test Result(s)

Tested Item(s)	Result	MDL
Polycyclic Aromatic Hydrocarbons (PAHs)		
Naphthalene	0.3 mg/kg	0.2 mg/kg
Acenaphthylene	N.D.	0.2 mg/kg
Acenaphthene	N.D.	0.2 mg/kg
Fluorene	N.D.	0.2 mg/kg
Phenanthrene	N.D.	0.2 mg/kg
Anthracene	N.D.	0.2 mg/kg
Fluoranthene	N.D.	0.2 mg/kg
Pyrene	N.D.	0.2 mg/kg
Benzo[a]anthracene	N.D.	0.2 mg/kg
Chrysene	N.D.	0.2 mg/kg
Benzo[b]fluoranthene	N.D.	0.2 mg/kg
Benzo[k]fluoranthene	N.D.	0.2 mg/kg
Benzo[a]pyrene	N.D.	0.2 mg/kg
Indeno[1,2,3-cd]pyrene	N.D.	0.2 mg/kg
Dibenzo[a,h]anthracene	N.D.	0.2 mg/kg
Benzo[g,h,i]perylene	N.D.	0.2 mg/kg
Benzo[j]fluoranthene	N.D.	0.2 mg/kg
Benzo[e]pyrene	N.D.	0.2 mg/kg
Sum (Acenaphthylene, Acenaphthene, Fluorene, Phenanthrene, Anthracene, Fluoranthene, Pyrene)	N.D.	/
Sum 18 PAHs	0.3 mg/kg	/

Tested Sample/Part Description Fluorescence yellow/White paper

Remark:


- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million

Test Report

Report No. SCL03J000377005

Page 4 of 5

Test Process



Test Report


Report No. SCL03J000377005

Page 5 of 5

Photo(s) of the sample(s)



Photo(s) for reference



At the request of client, the product(s) in this report is/are provided by applicant (non-tested sample(s)).

*** End of report ***

The test report is effective only with both signature and specialized stamp. The result(s) shown in this report refer only to the sample(s) tested. Without written approval of CTI, this report can't be reproduced except in full.